

## 試驗報告



報告編號：HB-18-08501

C-18-32657

頁數：1 OF 1

報告日期：107年11月09日

委託單位：峰奕股份有限公司  
 樣品名稱：Bona R880 矽烷(Silane)堅固彈性膠黏劑  
 送驗人員：峰奕股份有限公司(羅台禧)  
 收件日期：107年10月30日  
 試驗日期：107年11月01日~107年11月08日  
 備註：1. 以上資料由顧客提供(收件及試驗日期除外)  
 2. 除非另有說明，此報告結果僅對測試之樣品負責  
 未經本公司事先書面同意，此報告不可部分複製

### 試驗結果：

試體編號	接著強度 kgf/cm <sup>2</sup>		試驗方法
	標準養護 7 天	破壞位置	
1	14.9	A	參考 CNS 12611(2011)
2	16.4	A	
3	16.0	A	
4	15.3	A	
5	14.9	A	
平均	15.5	--	
規範要求值	平均值 6kgf/cm <sup>2</sup> 以上		

- 註：1. A 表示破壞位置為接著劑  
 2. 使用方式：黏著劑塗布完成後，立即黏貼面磚，不承壓 1 公斤之重錘。  
 3. 陶瓷面磚：由實驗室提供(CNS 9737 吸水率 III 類)  
 4. 墊底材係以水泥砂漿製成，配比(重量比)=台泥 I 型:標準砂:水=1:2:0.65  
 5. 養護條件：標準養護 168 小時(溫度 23±2°C；相對濕度 50±10%)。  
 6. 本試驗之樣品不在 TAF 認可範圍內，故無法出具 TAF 標誌之報告。

規範要求值僅供參考，合格之判定以委託單位實際要求為準。

  
 報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents](http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

